


PTFE Coated Fiberglass Yarn

600 deg. Fahrenheit
Intermittent to 1000 deg. F



316 deg. Celsius
Intermittent to 538 deg. C



Product Data					
Part #	Raw Glass Style	Yield Yds/Lb	Approx. Build (in.)	Approx. Yarn Diameter	Tensile (lbs)
12TXX-021	150 3/2	2,140	0.0112	0.0189	20.1
12TXX-032	150 2/2	3,200	0.0090	0.0153	13.9
12TXX-043	150 1/3	4,260	0.0077	0.0133	8.9
12TXX-064	150 1/2	6,450	0.0063	0.0109	6.3
12TXX-096	225 1/2	9,600	0.0052	0.0088	5.8
12TXX-190	450 1/2	19,300	0.0036	0.0063	2.7
12TXX-390	900 1/2	38,900	0.0026	0.0045	1.2
15TXX-021	150 3/2	2,065	0.0015	0.0194	20.1
15TXX-032	150 2/2	3,100	0.0092	0.0158	13.9
15TXX-043	150 1/3	4,150	0.0079	0.0137	8.9
15TXX-064	150 1/2	6,200	0.0064	0.0112	6.3
15TXX-096	225 1/2	9,300	0.0053	0.0091	5.8
15TXX-190	450 1/2	18,700	0.0037	0.0064	2.7
15TXX-390	900 1/2	37,500	0.0027	0.0046	1.2

Elongation of fiberglass yarn is typically less than 5%. **Operating Temperature:** Min -400 to Max 600 deg F. Intermittent to 1000 deg.F.
Packages Available include single or multiple end braider bobbins or bulk form.
Colors include white, black, blue, brown, gray, green, orange, red and yellow.
Values shown are typical and should not be used for writing specifications. All data is subject to change without notice.

W.F. Lake Corp.
P.O. Box 4214
65 Park Road
Glens Falls, NY 12804
Customer Service: (800) 428-1162
Tel: (518) 798-9934
Fax: (518) 798-9936

www.wflake.com
info@wflake.com