


PTFE Coated Beta (BC) Fiberglass Sewing Thread

1000 deg. Fahrenheit - Fiberglass
550 deg. Fahrenheit - PTFE



538 deg. Celsius - Fiberglass
288 deg. Celsius - PTFE



Product Data						
Product #	R751-12	R751-18	R753-12	R753-18	R753-24	R753-27
Thread Style	- Continuous Filament Beta (BC) Glass Fiber -					
Coating Type	-PTFE, Sintered-					
Coating %	18	18	12	12	12	12
Yield (yds/lb)	2850	1900	3000	2000	1500	1050
Tensile (lbs)	12	18	12	18	25	30
Diameter (nom)	0.016"	0.019"	0.015"	0.018"	0.021"	0.024"
Final Twist	"Z"	"Z"	"Z"	"Z"	"Z"	"Z"
Color	-Natural, Tan-					
Serving Package: King Spool			Operating Temp: 1000 deg. F. (538 deg. C.)			
Approx. Net Wt.: 2 lb/spool (others available)			(PTFE Coating to 550 deg. F)			
Available with high speed silicone thread lubricant applied in line.						
All values are typical and should not be used for writing specifications.						

W.F. Lake Corp.

P.O. Box 4214
65 Park Road
Glens Falls, NY 12804
Customer Service: (800) 428-1162
Tel: (518) 798-9934
Fax: (518) 798-9936

www.wflake.com
info@wflake.com