


## PTFE Coated Quartz Sewing Thread

2000 deg. Fahrenheit - Fiberglass  
550 deg. Fahrenheit - PTFE



1100 deg. Celsius - Fiberglass  
288 deg. Celsius - PTFE



<b>Product Data</b>					
Product #	TFQ-12	TFQ-18	TFQ-24	TFQ-27	TFQ-30
Thread Style	- Continuous Filament Pure Fused Silica -				
Coating Type	-PTFE, Sintered-				
Coating %	20	20	20	20	20
Yield (yds/lb)	2950	1975	1475	920	635
Tensile (lbs)	12	20	24	27	30
Diameter (nom)	0.014"	0.017"	0.021"	0.024"	0.028"
Final Twist	"Z"	"Z"	"Z"	"Z"	"Z"
Color	-Natural, Tan-				
Serving Package: King Spool			Operating Temp: 2000 deg. F. (538 deg. C.)		
Approx. Net Wt.: 1 lb/spool (others available)			(PTFE Coating to 550 deg. F)		
Available with high speed silicone thread lubricant applied in line.					
<b>All values are typical and should not be used for writing specifications.</b>					

**W.F. Lake Corp.**

P.O. Box 4214  
65 Park Road  
Glens Falls, NY 12804  
Customer Service: (800) 428-1162  
Tel: (518) 798-9934  
Fax: (518) 798-9936

[www.wflake.com](http://www.wflake.com)  
[info@wflake.com](mailto:info@wflake.com)