


PTFE Coated Aramid* / Stainless Thread

500 deg. Fahrenheit - Kevlar
 1000 deg. Fahrenheit –Stainless Steel Wire



260 deg. Celsius - Kevlar
 538 deg. Celsius – Stainless Steel Wire



| Product Data | | | | |
|---|---------------------------------|---|----------------|-----------------|
| Product # | R722-70 | R721-70 | R721-73 | R721-710 |
| Thread Style | - Kevlar* Continuous Filament - | | | |
| Coating Type | -PTFE, Sintered- | | | |
| Stainless Steel Wire | No Wire | 1 wire | 3 wires | 10 wires |
| Coating % | 12 | 12 | 12 | 12 |
| Yield (yds/lb) | 5000 | 4500 | 3500 | 1450 |
| Tensile (lbs) | 25 | 25 | 25 | 25 |
| Diameter (nom) | 0.010" | 0.011" | 0.014" | 0.024" |
| Final Twist | "Z" | "Z" | "Z" | "Z" |
| Color | -Natural, Tan- | | | |
| Serving Package: King Spool | | Operating Temp: Kevlar to 500 deg. F | | |
| Approx. Net Wt.: 1 lb/spool (others available) | | (Stainless Steel wire to over 1000 deg. F) | | |
| Available with high speed silicone thread lubricant applied in line. | | | | |
| All values are typical and should not be used for writing specifications. *Kevlar Reg. DuPont | | | | |

W.F. Lake Corp.

P.O. Box 4214
 65 Park Road
 Glens Falls, NY 12804
 Customer Service: (800) 428-1162
 Tel: (518) 798-9934
 Fax: (518) 798-9936

www.wflake.com
info@wflake.com