




High Performance PTFE & Silicone Coated Products

Uncoated ASTM D4030 Fiberglass Sewing Thread

975 deg. Fahrenheit



510 deg. Celsius



| Product Data | | | |
|--|---|--|------------------|
| ASTM#/Product # | T-12/DE-4 | T-18/DE-6 | T-24/DE-8 |
| Thread Style | - Continuous Filament ECDE GlassFiber - | | |
| Coating Type | -Uncoated, Raw Fiberglass- | | |
| Coating % | -Not Applicable- | | |
| Yield (yds/lb) | 3550 | 2330 | 1730 |
| Tensile (lbs) | 13 | 20 | 25 |
| Diameter (nom) | 0.014" | 0.017" | 0.020" |
| Final Twist | "Z" | "Z" | "Z" |
| Color | -Natural, White- | | |
| Serving Package: King Spool | | Operating Temp: 975 deg. F. (510 deg. C.) | |
| Approx. Net Wt.: 2 lb/spool (others available) | | | |
| Available with high speed silicone thread lubricant applied in line. | | | |
| All values are typical and should not be used for writing specifications. | | | |

W.F. Lake Corp.

P.O. Box 4214
 65 Park Road
 Glens Falls, NY 12804
 Customer Service: (800) 428-1162
 Tel: (518) 798-9934
 Fax: (518) 798-9936

www.wflake.com
info@wflake.com