




High Performance PTFE & Silicone Coated Products

Uncoated ASTM D4030 Fiberglass Sewing Thread

975 deg. Fahrenheit



510 deg. Celsius



Product Data			
ASTM#/Product #	T-12/DE-4	T-18/DE-6	T-24/DE-8
Thread Style	- Continuous Filament ECDE GlassFiber -		
Coating Type	-Uncoated, Raw Fiberglass-		
Coating %	-Not Applicable-		
Yield (yds/lb)	3550	2330	1730
Tensile (lbs)	13	20	25
Diameter (nom)	0.014"	0.017"	0.020"
Final Twist	"Z"	"Z"	"Z"
Color	-Natural, White-		
Serving Package: King Spool		Operating Temp: 975 deg. F. (510 deg. C.)	
Approx. Net Wt.: 2 lb/spool (others available)			
Available with high speed silicone thread lubricant applied in line.			
All values are typical and should not be used for writing specifications.			

W.F. Lake Corp.

P.O. Box 4214
 65 Park Road
 Glens Falls, NY 12804
 Customer Service: (800) 428-1162
 Tel: (518) 798-9934
 Fax: (518) 798-9936

www.wflake.com
info@wflake.com