


PTFE Coated Quartz Sewing Thread

2000 deg. Fahrenheit - Fiberglass
550 deg. Fahrenheit - PTFE



1100 deg. Celsius - Fiberglass
288 deg. Celsius - PTFE



| Product Data | | | | | |
|--|---|--------|---|--------|--------|
| Product # | TFQ-12 | TFQ-18 | TFQ-24 | TFQ-27 | TFQ-30 |
| Thread Style | - Continuous Filament Pure Fused Silica - | | | | |
| Coating Type | -PTFE, Sintered- | | | | |
| Coating % | 20 | 20 | 20 | 20 | 20 |
| Yield (yds/lb) | 2950 | 1975 | 1475 | 920 | 635 |
| Tensile (lbs) | 7 | 20 | 24 | 27 | 30 |
| Diameter (nom) | 0.014" | 0.017" | 0.021" | 0.024" | 0.028" |
| Final Twist | "Z" | "Z" | "Z" | "Z" | "Z" |
| Color | -Natural, Tan- | | | | |
| Serving Package: King Spool | | | Operating Temp: 200 deg. F. (538 deg. C.) | | |
| Approx. Net Wt.: 1 lb/spool (others available) | | | (PTFE Coating to 550 deg. F) | | |
| Available with high speed silicone thread lubricant applied in line. | | | | | |
| All values are typical and should not be used for writing specifications. | | | | | |

W.F. Lake Corp.

P.O. Box 4214
65 Park Road
Glens Falls, NY 12804
Customer Service: (800) 428-1162
Tel: (518) 798-9934
Fax: (518) 798-9936

www.wflake.com
info@wflake.com