




High Performance PTFE & Silicone Coated Products

PTFE Coated S2 Glass Fiber /Stainless Steel Insert Sewing Thread

1400 deg. Fahrenheit – Fiberglass
1600 deg. F – Stainless Steel Wire



760 deg. Celsius – Fiberglass
871 deg. C – Stainless Steel Wire



Product Data				
Product #	SGT-12/SS	SGT-18/SS	SGT-24/SS	SGT-27/SS
Thread Style	- S-2 Glass Fiber with integral Stainless Steel Wire -			
Coating Type	-PTFE, Sintered-			
Coating %	15	15	15	15
Yield (yds/lb)	2950	1975	1475	920
Tensile (lbs)	12	18	25	30
Diameter (nom)	0.016"	0.019"	0.023"	0.031"
Final Twist	"Z"	"Z"	"Z"	"Z"
Color	-Natural, Tan-			
Serving Package: King Spool		Operating Temp: 1400 deg. F. (760 deg. C.)		
Approx. Net Wt.: 2 lb/spool (others available)		(PTFE Coating to 600 deg. F)		
Available with high speed silicone thread lubricant applied in line.				
All values are typical and should not be used for writing specifications.				

W.F. Lake Corp.

P.O. Box 4214
65 Park Road
Glens Falls, NY 12804
Customer Service: (800) 428-1162
Tel: (518) 798-9934
Fax: (518) 798-9936

www.wflake.com
info@wflake.com