

High Performance PTFE & Silicone Coated Products

## PTFE Coated Quartz Tie Cord

2000 deg. Fahrenheit - Fiberglass 550 deg. Fahrenheit - PTFE



1075 deg. Celsius - Fiberglass 288 deg. Celsius - PTFE



Product Data		
Product #	Q761-540	
Coating Type	- PTFE, Unsintered -	
Braid Type	-Round-	
Yield (yds/lb)	345	
Thickness (in.)	n/a	
Width (in.)	n/a	
Diameter (in.)	.050	
Tensile (lb/min)	65	
Package Size (yds)	250 Yds	

Elongation of tie cord is typically less than 5%. Operating Temps. 2000 deg. F –Fiberglass / 550 deg. F –PTFE

**Colors** other than natural may require minimum purchase quantity. Approx. 25% tensile strength loss with colors. Please consult the factory. **Dimensions** shown are nominal, however most are within 10%. Consult factory as needed.

W.F. Lake Corp.
P.O. Box 4214
65 Park Road
Glens Falls, NY 12804

Customer Service: (800) 428-1162

Phone: (518) 798-9934 Fax: (518) 798-9936