




High Performance PTFE & Silicone Coated Products

# PTFE Coated Beta (BC) Fiberglass Sewing Thread

1000 deg. Fahrenheit - Fiberglass  
 550 deg. Fahrenheit - PTFE



538 deg. Celsius - Fiberglass  
 288 deg. Celsius - PTFE



<b>Product Data</b>						
Product #	R751-12	R751-18	R753-12	R753-18	R753-24	R753-27
Thread Style	- Continuous Filament Beta (BC) Glass Fiber -					
Coating Type	-PTFE, Sintered-					
Coating %	18	18	12	12	12	12
Yield (yds/lb)	2850	1900	3000	2000	1500	1050
Tensile (lbs)	12	18	12	18	25	30
Diameter (nom)	0.016"	0.019"	0.015"	0.018"	0.021"	0.024"
Final Twist	"Z"	"Z"	"Z"	"Z"	"Z"	"Z"
Color	-Natural, Tan-					
Serving Package: King Spool			Operating Temp: 1000 deg. F. (538 deg. C.)			
Approx. Net Wt.: 2 lb/spool (others available)			(PTFE Coating to 550 deg. F)			
Available with high speed silicone thread lubricant applied in line.						
<b>All values are typical and should not be used for writing specifications.</b>						

**W.F. Lake Corp.**  
 P.O. Box 4214  
 65 Park Road  
 Glens Falls, NY 12804  
 Customer Service: (800) 428-1162  
 Tel: (518) 798-9934  
 Fax: (518) 798-9936  
[www.wflake.com](http://www.wflake.com)  
[info@wflake.com](mailto:info@wflake.com)

**Important Processing Information.**

W.F. Lake Corp. PTFE coated fiberglass and aramid sewing threads are coated during manufacture with sizing's or finishes, including PTFE, to serve as aids in textile processing. When these products are heated above the continuous operating temperature of PTFE (550 degrees F, 287 degrees C), adequate ventilation and /or personal protective equipment must be used in accordance with site-specific exposure assessment as vapors can be emitted and may be hazardous if inhaled. See Safety Data Sheet or contact W.F. Lake Corp. for more information.