




High Performance PTFE & Silicone Coated Products

PTFE Coated "E-Glass" Fiberglass Sewing Thread

1000 deg. Fahrenheit - Fiberglass
 550 deg. Fahrenheit - PTFE



538 deg. Celsius - Fiberglass
 288 deg. Celsius - PTFE



| Product Data | | | |
|--|--|--|---------|
| Product # | R753-12 | R753-18 | R753-24 |
| Thread Style | - Continuous Filament Beta (BC) Fiber - | | |
| Coating Type | -PTFE, Sintered- | | |
| Coating % | 15 | 15 | 15 |
| Yield (yds/lb) | 3000 | 2000 | 1500 |
| Tensile (lbs) | 12 | 18 | 25 |
| Diameter (nom) | 0.015" | 0.018" | 0.021" |
| Final Twist | "Z" | "Z" | "Z" |
| Color | -Red, Blue, Green, Orange, Black, Brown- | | |
| Serving Package: King Spool | | Operating Temp: 1000 deg. F. (540 deg. C.) | |
| Approx. Net Wt.: 2 lb/spool (others available) | | (PTFE Coating to 550 deg. F) | |
| Available with high speed silicone thread lubricant applied in line. | | | |
| All values are typical and should not be used for writing specifications. | | | |
| PN Example: R753-18LRED: X80 Lubricated, Red Color Thread | | | |

W.F. Lake Corp.
 P.O. Box 4214
 65 Park Road
 Glens Falls, NY 12804
 Customer Service: (800) 428-1162
 Tel: (518) 798-9934
 Fax: (518) 798-9936
www.wflake.com
info@wflake.com

Important Processing Information.

W.F. Lake Corp. PTFE coated fiberglass and aramid sewing threads are coated during manufacture with sizing's or finishes, including PTFE, to serve as aids in textile processing. When these products are heated above the continuous operating temperature of PTFE (550 degrees F, 287 degrees C), adequate ventilation and / or personal protective equipment must be used in accordance with site-specific exposure assessment as vapors can be emitted and may be hazardous if inhaled. See Safety Data Sheet or contact W.F. Lake Corp. for more information.