


PTFE Coated “E-Glass” Fiberglass Sewing Thread

1000 deg. Fahrenheit



538 deg. Celsius - Fiberglass



Product Data				
Product #	R783-12	R783-18	R783-24	R783-27
Thread Style	- Continuous Filament “E-Glass Fiber -			
Coating Type	-PTFE, Sintered-			
Coating %	12	12	12	12
Yield (yds/lb)	3000	2000	1500	1050
Tensile (lbs)	12	18	25	30
Diameter (nom)	0.015”	0.018”	0.021”	0.024”
Final Twist	“Z”	“Z”	“Z”	“Z”
Color	-Natural, Tan-			
Serving Package: King Spool Operating Temp: 550 deg. Continuous, 1000 deg. F. intermittent. Approx. Net Wt.: 2 lb/spool (others available) (290 deg. C continuous) , (540 deg. C intermittent) Available with high speed silicone thread lubricant applied in line. All values are typical and should not be used for writing specifications.				

W.F. Lake Corp.

P.O. Box 4214
 65 Park Road
 Glens Falls, NY 12804
 Customer Service: (800) 428-1162
 Tel: (518) 798-9934
 Fax: (518) 798-9936
www.wflake.com
info@wflake.com

Important Processing Information.

W.F. Lake Corp. PTFE coated fiberglass and aramid sewing threads are coated during manufacture with sizing's or finishes, including PTFE, to serve as aids in textile processing. When these products are heated above the continuous operating temperature of PTFE (550 degrees F, 287 degrees C), adequate ventilation and /or personal protective equipment must be used in accordance with site-specific exposure assessment as vapors can be emitted and may be hazardous if inhaled. See Safety Data Sheet or contact W.F. Lake Corp. for more information.