




High Performance PTFE & Silicone Coated Products

# PTFE Coated S2 Glass Fiber /Stainless Steel Insert Sewing Thread

1400 deg. Fahrenheit – Fiberglass  
1600 deg. F – Stainless Steel Wire



760 deg. Celsius – Fiberglass  
871 deg. C – Stainless Steel Wire



<b>Product Data</b>				
<b>Product #</b>	<b>SGT-12/SS</b>	<b>SGT-18/SS</b>	<b>SGT-24/SS</b>	<b>SGT-27/SS</b>
<b>Thread Style</b>	- S-2 Glass Fiber with integral Stainless Steel Wire -			
<b>Coating Type</b>	-PTFE, Sintered-			
<b>Coating %</b>	15	15	15	15
<b>Yield (yds/lb)</b>	2950	1975	1475	920
<b>Tensile (lbs)</b>	20	25	29	40
<b>Diameter (nom)</b>	0.016"	0.019"	0.023"	0.031"
<b>Final Twist</b>	"Z"	"Z"	"Z"	"Z"
<b>Color</b>	-Natural, Tan-			
<b>Serving Package:</b> King Spool		<b>Operating Temp:</b> 1400 deg. F. (760 deg. C.)		
<b>Approx. Net Wt.:</b> 2 lb/spool (others available)		(PTFE Coating to 550 deg. F)		
Available with high speed silicone thread lubricant applied in line.				
<b>All values are typical and should not be used for writing specifications.</b>				

**W.F. Lake Corp.**  
P.O. Box 4214  
65 Park Road  
Glens Falls, NY 12804  
Customer Service: (800) 428-1162  
Tel: (518) 798-9934  
Fax: (518) 798-9936  
[www.wflake.com](http://www.wflake.com)  
[info@wflake.com](mailto:info@wflake.com)

### Important Processing Information.

W.F. Lake Corp. PTFE coated fiberglass and aramid sewing threads are coated during manufacture with sizing's or finishes, including PTFE, to serve as aids in textile processing. When these products are heated above the continuous operating temperature of PTFE (550 degrees F, 287 degrees C), adequate ventilation and /or personal protective equipment must be used in accordance with site-specific exposure assessment as vapors can be emitted and may be hazardous if inhaled. See Safety Data Sheet or contact W.F. Lake Corp. for more information.