




High Performance PTFE & Silicone Coated Products

PTFE Coated Quartz Sewing Thread

2000 deg. Fahrenheit - Quartz
 550 deg. Fahrenheit - PTFE



1100 deg. Celsius - Quartz
 288 deg. Celsius - PTFE



Product Data					
Product #	TFQ-12	TFQ-18	TFQ-24	TFQ-27	TFQ-30
Thread Style	- Continuous Filament Pure Fused Silica -				
Coating Type	-PTFE, Sintered-				
Coating %	20	20	20	20	20
Yield (yds/lb)	2950	1975	1475	920	635
Tensile (lbs)	7	20	24	27	30
Diameter (nom)	0.014"	0.017"	0.021"	0.024"	0.028"
Final Twist	"Z"	"Z"	"Z"	"Z"	"Z"
Color	-Natural, Tan-				
Serving Package: King Spool Approx. Net Wt.: 1 lb/spool (others available) Available with high speed silicone thread lubricant applied in line. All values are typical and should not be used for writing specifications.			Operating Temp: 2000 deg. F. (538 deg. C.) (PTFE Coating to 550 deg. F)		

W.F. Lake Corp.
 P.O. Box 4214
 65 Park Road
 Glens Falls, NY 12804
 Customer Service: (800) 428-1162
 Tel: (518) 798-9934
 Fax: (518) 798-9936
www.wflake.com
info@wflake.com

Important Processing Information.

W.F. Lake Corp. PTFE coated fiberglass and aramid sewing threads are coated during manufacture with sizing's or finishes, including PTFE, to serve as aids in textile processing. When these products are heated above the continuous operating temperature of PTFE (550 degrees F, 287 degrees C), adequate ventilation and / or personal protective equipment must be used in accordance with site-specific exposure assessment as vapors can be emitted and may be hazardous if inhaled. See Safety Data Sheet or contact W.F. Lake Corp. for more information.

