




High Performance PTFE & Silicone Coated Products

PTFE Coated Fiberglass Lacing Tape and Tie Cord

550 deg. Fahrenheit



287 deg. Celsius



Product Data									
Product #	-E779 Series-					-E761 Series-			
		-222	-303	-476	-680	-1075	-314	-668	-1330
Coating Type	- PTFE, Unsintered -								
Braid Type	-Flat-					-Round-			
Yield (yds/lb)	220	325	520	430	1025	360	540	1150	
Thickness (in.)	.018	.015	.011	.013	.007	n/a	n/a	n/a	
Width (in.)	1/8	7/64	3/32	5/64	3/64	n/a	n/a	n/a	
Diameter (in.)	n/a	n/a	n/a	n/a	n/a	.047	.034	.027	
Tensile (lb/min)	125	100	90	60	40	80	75	50	
Package Size (yds)	250 Yds	all others 250 or 500 yard spools-							
<p>Elongation of lacing tape and tie cord is typically less than 5%. Operating Temps. 550 deg. F</p> <p>Colors other than natural may require minimum purchase quantity. Approx. 25% tensile strength loss with colors. Please consult the factory.</p> <p>Dimensions shown are nominal, however most are within 10%. Consult factory as needed.</p>									

W.F. Lake Corp.

P.O. Box 4214
 65 Park Road
 Glens Falls, NY 12804
 Customer Service: (800) 428-1162
 Tel: (518) 798-9934
 Fax: (518) 798-9936
www.wflake.com
info@wflake.com

Important Processing Information.

W.F. Lake Corp. PTFE coated fiberglass and aramid sewing threads are coated during manufacture with sizing's or finishes, including PTFE, to serve as aids in textile processing. When these products are heated above the continuous operating temperature of PTFE (550 degrees F, 287 degrees C), adequate ventilation and / or personal protective equipment must be used in accordance with site-specific exposure assessment as vapors can be emitted and may be hazardous if inhaled. See Safety Data Sheet or contact W.F. Lake Corp. for more information.